

BOW-LITE™ (E)

Single Mode Optical Fibre ITU-T G.657.A2

Product Description

BOW-LITE™ (E) Single Mode Optical Fibre is a single mode optical fibre with ultra-low bend sensitivity

Product Application

BOW-LITE™ (E) fibre is designed to substantially reduce bend losses and hence deliver better performance in tight bend scenarios and efficient functioning at higher wavelengths

Product Benefits

BOW-LITE™ (E) fibre changes the paradigm of optical networks by combining enhanced macro bend performance with a score of functional benefits like, optimised power budgets, hardware miniaturisation and installation agility. This high performance optical fibre can be seamlessly integrated with the legacy network built on G.652.D fibre.

Extensive experiments prove that by using BOW LITE (E), tangible benefits accrue in terms of enhanced network longevity by a minimum of 10+ years especially in emerging markets

Product Specifications

Attenuation (Typical Values)	≤ 0.34 dB/km at 1310 nm ≤ 0.20 dB/km at 1550 nm ≤ 0.22 dB/km at 1625 nm
Mode field diameter	8.6 ± 0.4 μ m at 1310 nm
Cable cutoff wavelength	≤ 1260 nm
Zero dispersion wavelength	1300 nm to 1324nm
Zero dispersion slope	≤ 0.092 ps/nm ² .km
Dispersion at 1550 nm	≤ 18.0 ps/nm.km
PMD Individual Fibre*	≤ 0.1 ps/ \sqrt km
PMD LDV	≤ 0.06 ps/ \sqrt km
Cladding diameter	125 ± 0.7 μ m
Core-clad concentricity error	≤ 0.5 μ m
Cladding non-circularity	≤ 0.8 %
Coating diameter	242 ± 5 μ m
Coating-cladding concentricity error	≤ 10 μ m

* Individual PMD values may change when cabled

Mechanical Characteristics

Proof Test Levels	≥ 100 kpsi (0.7GN/m ²). This is equivalent to 1% strain
Coating strip force(Force to mechanically strip the dual coating)	≥ 1.3 N (0.3 lbf) and ≤ 5.0 N (1.1lbf)
Fibre curl	≥ 4 m

Macro bend loss: The maximum attenuation with bending does not exceed the specified values with the following deployment conditions

Deployment condition	Wavelength	Induced attenuation
10 turn, 15 mm radius 10 turn, 15 mm radius	1550 nm 1625 nm	≤ 0.03 dB ≤ 0.10 dB
1 turn, 10 mm radius 1 turn, 10 mm radius	1550 nm 1625 nm	≤ 0.10 dB ≤ 0.20 dB
1 turn, 7.5 mm radius 1 turn, 7.5 mm radius	1550 nm 1625 nm	≤ 0.20 dB ≤ 0.50 dB

Environmental Characteristics

Temperature dependence Induced attenuation, -60°C to +85°C at 1310, 1550, 1625 nm	≤ 0.05 dB/km
Temperature humidity cycling Induced attenuation, -10°C to +85°C and 95% relative humidity at 1310, 1550, 1625 nm	≤ 0.05 dB/km
High temperature and humidity aging 85°C at 85% RH, 30 days Induced attenuation at 1310, 1550, 1625 nm due to aging	≤ 0.05 dB/km
Water immersion, 30 days Induced attenuation due to water immersion at 23±2°C at 1310, 1550, 1625 nm	≤ 0.05 dB/km
Accelerated aging (Temperature), 30days Induced attenuation due to temperature aging at 85±2°C at 1310,1550,1625 nm	≤ 0.05 dB/km

Other Performance Characteristics*

Effective group index of refraction	1.4678 at 1310 nm 1.4685 at 1550 nm 1.4689 at 1625 nm
Attenuation in the wavelength region from 1285 - 1330 nm in reference to the attenuation at 1310 nm	≤ 0.03 dB/km
Attenuation in the wavelength region from 1525 - 1575 nm in reference to the attenuation at 1550 nm	≤ 0.02 dB/km
Point discontinuities at 1310 nm & 1550 nm	≤ 0.05 dB
Dynamic fatigue parameter (Nd)	≥ 20
Shipping Length: Standard length per reel available up to 25.2 km	

*Typical values

Manufacturing Process

STL controls every stage of the manufacturing process so that quality is built in to every meter of fibre, rather than selected out at the end through testing. To ensure the accuracy and precision of the manufacturing process, STL routinely calibrates and recertifies process equipment and measurement benches against internationally traceable standards from NPL/NIST, and follow test methods compliant with EIA/TIA, CEI-IEC and ITU standards.

International Standards

STL BOW-LITE™ (E) complies or exceeds the ITU Recommendation G.652.D and G.657.A2 and the IEC 60793-2-50 type B6_a2 Optical Fibre Specification.

Service USP's

- Complete range of optical fibre for terrestrial networks
- World-wide sales support
- Web-based order tracking & customer support
- Specialized technical support

Disclaimer

STL's policy of continuous improvement may result in a change in specifications without prior notice. Any warranty of any nature relating to any STL product is only contained in the written agreement between STL and the direct purchaser of such product(s).

Issued: May 2019